

AC SEPAROL F1A

AC SEPAROL F1A is an interlevant powder based on polymethyl methacrylate and adipic acid for transport and storage of glass if a certain anti-stain/anti-weathering effect is required. It is normally used when powdering float glass on-line.

AC SEPAROL F1A has a medium particle size of approx. 65 µm.

The recommended application rate is 150 – 200 mg/m².

Specification

Acid number:	69 - 85	DGF C-V 2
Bulk density:	660 – 760 g/l	DGF H-II 1b
Particle size > 250 µm:	max 0,5 %	Laser Particle Analysis
Particle size < 20 µm:	max 5 %	Laser Particle Analysis
Medium particle size between:	54 – 80 µm	Laser Particle Analysis
Temperature resistance:	passed	AC MV 26 (80 °C, 30 min)

Handling

When handling AC SEPAROL F1A the use of safety gloves and a dust mask is recommended. For further safety advice please see our Material Safety Data Sheet.

Storage

Stored in well-closed containers at temperatures between 5 to 40 °C AC SEPAROL F1A has a shelf-life of minimum 1 year.